



PRODUCT DATA SHEET

9410 UHS CLEARCOAT

PRODUCT DESCRIPTION:

High gloss acrylic 2K clearcoat. Excellent gloss, easy to handle, suitable for partial and overall repairs.

SUBSTRATES:

1K Solvent based Basecoat system. 1K Waterborne Basecoat system. 2K Acryl Paint Systems.

SUBSTRATE PREPARATION:

Surfaces must be clean, dry, and free of rust, dust and grease.
Before the application use **9651** Degreaser.

APPLICATION:



Always wear protective equipment



2 parts 9410
1 part 9511 SLOW / 9512 STANDARD / 9513 FAST



10% 9612 STANDARD



17 - 19s
DIN 4 / 20°C (68°F)



1.3 – 1.4 mm
2 - 3 bar (29 - 44 psi)
2x = 50 - 60 µm



HVLP 1.2 – 1.3 mm
2 bar (29 psi)
2x = 50 - 60 µm



5 - 10 min / 23°C (73°F)



8 - 16 hrs / 23°C (73°F)
20 - 30 min / 60°C (140°F)

PRODUCT DATA SHEET

9410 UHS CLEARCOAT



8 – 12 min (60 - 70 cm)



1K - 2K Acryl Primers

EQUIPMENT CLEANING:

After use, clean all equipment thoroughly with Nitro Thinner.

TYPICAL PRODUCT DATA:

FLASH POINT: 24°C / 75°F

SPECIFIC GRAVITY: 0.985 g/cm³

SOLIDS CONTENT: 50%

THEORETICAL COVERAGE: N/A

VOC INFORMATION: 2004/42/IIIB(e) (840)840

COLOUR: TRANSPARENT

PACKSIZE: 1L, 5L

STORAGE CONDITIONS: Store in cool place (5°- 25°C), avoid direct exposure to sunlight.

SHELF LIFE: 24 months in tightly closed containers.

For professional use only! These products are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps to ensure the suitability of the product for the intended purpose. We are not liable for its correctness, accuracy and completeness.

All rights reserved. The user of this product should use the product in accordance with the laws and regulations for safety at work and waste management. We reserve the right to modify and to complete the information content at any time, without prior notice or obligation to update.

JUNE 2023